

Product Data Sheet

GMA ClassicCut™ 60



Average Chemical Composition (Typical)

SiO ₂ *	36%
Al ₂ O ₃	20%
Fe ₂ O ₃	35%
MgO	6%
CaO	2%
TiO ₂	3%
MnO	1%

*Refers to SiO₂ bound within the lattice of the homogeneous garnet crystal (not free silica)

Mineral Composition (Typical)

Garnet (predominately Almandine)	> 96%
Ilmenite	< 3%
Quartz (free silica)	< 0.1%
Other	< 1%

Product Range (typical weight % retained)

Mesh	Microns	Cumulative	Discrete
40	425	0.2	0
45	355	7	6.8
50	300	30	23
60	250	52	22
70	212	80	28
80	180	95	15
100	150	98	3
PAN	PAN	100	2

Physical Characteristics (Typical)

Bulk Density	2.3 T/m ³
Specific Gravity	4.1
Hardness (Mohs)	7.5 – 8.0
Melting Point	1250°C / 2250°F
Shape of Natural Grains	Sub-Angular

Other Characteristics (Typical)

Radioactivity	Non-detectable above background
Moisture Absorption	Non-hygroscopic, Inert
Total Chlorides	10 - 20 ppm
Conductivity	100 – 150 µS/cm (10 – 15 mS/m)

Packaging

- 25kg bags shrink wrapped onto a 1 metric ton or 2 metric ton pallet
- Loose bulk form in 1 metric ton or 2 metric ton bulk bag with an inner plastic liner on a pallet.

Source

- Made in Australia
- Product Code: GMA-AUS 60